

multicover®

RoHS Declaration

All steel products supplied by voestalpine in 2026 comply with Directive 2011/65/EU (RoHS 2) as well as Delegated Directive 2015/863/EU (RoHS 3) amending Annex II and Directive 2018/741 amending Annex III of Directive 2011/65/EU.

Dimensions

Thickness: 0.4 – 4.0 mm

Width: 900 – 1,600 mm

Not all thickness and width combinations are available.

Surface

Z

Technical data

Property	Test/test specification	Requirements
Corrosion protection	Neutral salt spray testing pursuant to DIN EN ISO 9227	< 5 % after 168 h
Corrosion protection	Cyclic humidity test DIN EN ISO 6270-2 AHT	< 1 % after 700 h
Resistance to solvents	100 double strokes with isopropanol	< 10 % coating loss
Resistance to hand sweat	Immersion in synthetic hand sweat solution for 10 s	< 10 % coating loss, no color change
Forming properties	Friction coefficient by means of POD measurement	$\mu < 0.13$
Powder coating adhesion	Grid cut according to 400 h climate test DIN EN ISO 6270-2-CH	Dry adhesion: GT 0 Wet adhesion: GT 0-2
Temperature stability	220 °C for 200 h	No peeling, no yellowing, no staining

Processing recommendations

Cleaning: Solvents (polar and non-polar) suitable for removing residues.

Washability: Removal with strong alkaline cleaners possible.

Forming: Dry forming possible without oil (roll forming, embossing, deep drawing, flanging), compatible with forming emulsions.

Joining: Good welding suitability (spot, projection, laser, brazing) as well as very good adhesion for powder coatings, PU foam and adhesive tapes.

General note

The information is based on internal voestalpine laboratory tests. Deviations may occur as a result of varying application and environmental conditions. It is recommended to separately verify suitability for the specific application case.

The information and product properties contained in this printed material are non-binding and serve the exclusive purpose of technical orientation. They do not replace individual consultation provided by our sales and customer service teams. The information and product properties provided in this fast sheet shall not be deemed guaranteed characteristics unless this has been agreed upon individually. Technical changes reserved. Errors and misprints excepted. No part of this publication may be reprinted without explicit written permission by voestalpine Stahl GmbH.

To find out more about
functional surfaces, please visit us at
www.voestalpine.com/functional-surfaces



voestalpine Steel Division

voestalpine-Straße 3
4020 Linz, Austria
productmanagement@voestalpine.com
www.voestalpine.com/steel

voestalpine

ONE STEP AHEAD.