

COLD WORK STEELS

Available Product Shapes

Flat Bar	Ground Flat	Long Products	Plates	Round Bar
Round Ground Bar				

Product Description

Punches and dies for blanking, piercing, cold heading and cold extrusions. Cold forming rolls. Knives for slitting, pelletizing and woodworking. Screws, nozzles and barrel liners for plastics compounding and injection moulding. Powder metal compaction tooling.

Properties

Powder-metallurgical produced cold work tool steel with extremely high wear resistance, good toughness and high compressive strength.

Applications

- > Machine knife (for producers)
- > Cold Forming
- > Fine Blanking, Stamping, Blanking
- > Screws and Barrels
- > General Components for Mechanical Engineering

Material designation	
1.2395	SEL
T30111	UNS
PM A11	AISI

Chemical composition

C	Si	Mn	Cr	Mo	V
2.45	0.90	0.50	5.20	1.30	9.50

Material characteristics

	Compressive strength	Dimensional stability during heat treatment	Toughness	Wear resistance abrasive	Wear resistance adhesive
	★★★★★	★★★★★	★★★	★★★★★	★★★★★
	★★	★★	★	★★★	★★
	★★	★★	★	★★	★★
	★★	★★	★	★★★	★★
	★★	★★★	★	★★★	★★
	★★★★	★★★★★	★★★★	★★★★	★★★★
	★★★	★★★★	★★★	★★★	★★★★
	★★★	★★★	★★	★★	★★
	★★★	★★★★	★★★	★★★★	★★★★
	★★★	★★★	★★★	★★★★	★★
	★★	★★★	★★	★★	★★
	★★★★★	★★★★★	★★★★	★★★★★	★★★★★
	★★★★	★★★★★	★★★★★	★★★	★★★
	★★★★	★★★★★	★★★★	★★★★	★★★★
	★★★★★	★★★★★	★★★	★★★★★	★★★★★

Delivery condition

Annealed

Hardness	max. 277 HB
----------	-------------

Heat treatment

Annealing

Temperature (°C / °F)	870 / 1598 - 540 / 1004	Protect steel from scaling and/or decarburization. Heat through to 1600°F (870°C). Control cool at 30°F (15°C) maximum per hour to 1000°F (540°C), then furnace or air cool to room temperature.
-----------------------	-------------------------	--

Stress relieving

Temperature (°C / °F)	700 / 1292 - 540 / 1004	If required after Rough machining to minimize distortion during final heat treatment, heat to 1100-1300°F (595-700°C) and hold for 2 hrs followed by furnace. Cool slowly to 930°F (500°C), then air cool.
-----------------------	-------------------------	--

Physical Properties at 20°C / 68°F

Density	7.42 / 0.27	[kg/dm ³ / lb/in ³]
Thermal conductivity	20.39 / 11.78	[W/(m.K) / BTU (IT) ft/hr/ft ² /F]
Specific heat	460 / 109.87	[J/(kg.K) / BTU (IT) lb/F]
Modulus of elasticity	221 / 32.05	[10 ³ N/mm ² / 10 ³ ksi]

Thermal Expansions

Temperature (°C / °F)	93 / 199.4	260 / 500	427 / 800.6	593 / 1099.4
Thermal expansion (10 ⁻⁶ m/(m.K) / 10 ⁻⁶ inch/(inch.F))	10.7 / 5.944	11.1 / 6.167	11.8 / 6.556	12.3 / 6.833

For more information see www.voestalpine.com/boehler-edelstahl