

HEAT-RESISTING STEELS

Available Product Variants

Plates

Product Description

Heat treatment shops, Furnace and boiler construction, Glass, porcelain, enamel, cement and ceramic industries, Mechanical engineering, Petroleum industry

Applications



- > Components for Chemical plants (incl. LNG, FGD, Urea, LDPE, etc.)
- > Distributors for Component Applications
- > Flowlines & Connectors
- > Other Oil and Gas + CPI components
- > Shafts
- > Well Logging Tools
- > Components for Industrial Gas Compressors
- > Distributors or producers of standard parts without knowledge of final applications
- > Mechanical Engineering
- > Other Power Generation Components
- > Tubular Products, Flanges, Fittings
- > Wellhead, X-mas trees and Manifolds (incl. Tubing hangers), BOPs
- > CPI (incl. LNG, Urea)
- > Drilling tools and components
- > Other Components
- > Rolls
- > Well Completion Tools
- > Hot Rolling


Technical data

Material designation	
1.4876	SEL
X10NiCrAlTi32-21	EN
N08800	UNS
N08810	
N08811	
NCF 800 HTF	JIS
NCF 800 TF	
NCF 800	
NCF 800 TP	
NCF 800 TB	

Chemical composition (wt. %)

C	Si	Mn	Cr	Ni	Ti	Al
0.07	0.35	0.75	20.8	32	0.3	0.3





Physical Properties

Density	8	[kg/dm³]
Thermal conductivity	12	[W/(m.K)]
Specific heat	550	[kJ/kg K]
Spec. electrical resistance	1	[Ohm.mm²/m]
Modulus of elasticity	198	[10³N/mm²]

Thermal Expansions between 20°C | 68°F and ...

Temperature (°C)	200	400	600	800	1,000
Thermal expansion (10 ⁻⁶ m/(m.K))	15	16	17	17.5	18.5

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.