

ENGINEERING STEELS - MARTENSITIC PRECIPITATION HARDENING (MARAGING) STEELS

Application Segments

Aerospace

Available Product Variants

Long Products*

Plates

* Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Product Description

BÖHLER V300 covers a premium aircraft-quality, maraging alloy steel in the form of bars, forgings and stock for forging up through 10 inches (254.00 mm) inclusive in diameter or least distance between parallel sides.

In contrast to heat treatable steels its outstanding tensile properties are not due to a hardened structure with relatively high carbon content, but to precipitation of intermetallic phases from a ductile nickel bearing matrix containing almost no carbon.

These products have been used typically for parts requiring through hardening, without quenching, to a minimum yield strength of 270 ksi (1862 MPa) and where such parts may require welding during fabrication, but usage is not limited to such applications. E.g highly stressed components for the aircraft and rocket industries.

Process Melting

VIM + VAR

Applications

> Structural parts (Aerospace)

> Other Aerospace Components

Technical data

Material designation		Standards	
Maraging 300	Market grade	6514	AMS
1.6354	SEL		

Chemical composition (wt. %)

C	Si	Mn	P	S	Cr	Mo	Ni	Cu	Co	Ti	Al	B	Ca	Zr
max. 0.03	max. 0.10	max. 0.10	max. 0.010	max. 0.010	max. 0.50	4.60 to 5.20	18.00 to 19.00	max. 0.50	8.50 to 9.50	0.50 to 0.80	0.05 to 0.15	max. 0.004	max. 0.05	max. 0.02

Related to AMS 6514

Delivery condition

Solution annealed

Hardness (HRC)	max. 36 Above 12.7 mm diameter
----------------	----------------------------------

Solution annealed

Hardness (HRC)	max. 36 Max 12.7 mm diameter
Tensile Strength (MPa)	max. 1,103 Max 12.7 mm diameter

Round Bars and Wire Rod (if any)

Diameter mm			MOQ ex mill kg	Length m			Tolerance
ROLLED							
5.01	-	12.49	1,100	3.00	-	4.00	IT h/k 11
12.50	-	55.00	1,300	3.00	-	4.00	IT h/k 11
55.01	-	120.00	2,500	3.00	-	4.00	IT h/k 11
120.01	-	140.00	2,500	3.00	-	5.00	IT h/k 14
FORGED							
140.01	-	203.20	2,200	3.00	-	5.00	IT h/k 14

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.