

PLASTIC MOULD STEELS

HARDENABLE CORROSION RESISTANT STEEL

Application Segments

Mucegai din plastic

Available Product Variants

Long Products*

Plates

* Datele prezentate se referă exclusiv la produsele lungi. Vă rugăm să respectați explicațiile detaliate de la sfârșitul fișei tehnice (pdf).

Product Description

BÖHLER M340 ISOPLAST corresponds to a corrosion-resistant, martensitic chromium steel with improved wear resistance. This is ideal for the application area of glass fiber reinforced plastics. In addition, the BÖHLER M340 ISOPLAST is approved for food and beverage contact.

Process Melting

Topit în aer + refulat

Properties

- > Rezistență și ductilitate : good
- > Rezistență la uzură : high
- > Machinability : good
- > Stabilitatea dimensională : very high
- > Poluabilitate : good
- > Rezistență la coroziune : high
- > Micro-curățenie : high

Applications

- | | | |
|-----------------------------------------------------------------|-------------------------------------------------------|------------------------------|
| > Componente pentru prelucrarea alimentelor și hrana animalelor | > Turnare prin injecție | > Vytlačanie plastov |
| > Șuruburi și butoaie | > Piese standard (matrițe, plăci, pini, perforatoare) | > Industria ambalajelor |
| > Componente pentru afișaje | > Cuțite de mână personalizate | > Industria electronică |
| > Matrițe de perforare a pastilelor | > Materiale plastice ranforsate cu fibră de sticlă | > Bunuri de consum - general |
| > Cuțit de mașină (pentru producători) | > Cuțite industriale | > Cutting |
| > Grinding | > Packaging | > Extrusion |
| > Components | > Wear Applications | > Pumping |
| > Mineral Processing | | |

Chemical composition (wt. %)

C	Si	Mn	Cr	Mo	V	N
0.54	0.45	0.4	17.3	1.1	0.1	+

Material characteristics

	Corrosion resistance	Machinability in as supplied condition	Polishability	Toughness	Wear resistance
BÖHLER M340 ISOPLAST	★★★	★★★	★★	★★	★★★
BÖHLER M310 ISOPLAST	★★★★	★★★★	★★	★★	★★
BÖHLER M333 ISOPLAST	★★★★★	★★★★	★★★★★	★★★★★	★★
BÖHLER M368 MICROCLEAN	★★★★	★★★	★★★★	★★★	★★★
BÖHLER M390 MICROCLEAN	★★	★	★★★	★★	★★★★★
BÖHLER M398 MICROCLEAN	★★	★	★★	★★	★★★★★
BÖHLER M380 ISOPLAST	★★★★★	★★★★	★★★★★	★★★★	★★★

Delivery condition

Recoaptă moale	
Hardness (HB)	max. 260

Heat treatment

Eliminarea stresului		
Temperature	max. 650 °C	Soft annealed material: For stress relief annealing after mechanical processing, hold the material at temperature in a neutral atmosphere for 1-2 hours after complete heating, then slowly cool the furnace at 20°C [68 °F]/hour to 200°C [392 °F], then cool in air.
Temperature		Hardened and tempered material: The temperature for stress relief annealing should be approx. 50°C [122 °F] below the previously selected tempering temperature. Other procedure as for stress relief annealing of soft annealed material.

Călire și revenire

Temperature	980 to 1,000 °C	For hardening, hold the material at the specified temperature for 15-30 minutes after complete heating and quench quickly. Cool the material to approx. 30°C [86 °F]. Immediately afterwards, the material can be deep-frozen for 2 hours (at -80°C [-112 °F]) for residual austenite transformation. Tempering should also be carried out immediately.
Temperature	250 to 350 °C	Tempering treatment: For maximum corrosion resistance, temper the material once for 1 hour/20 mm material thickness, but for at least 2 hours. Achievable hardness - see tempering diagram.
Temperature	505 to 520 °C	Tempering treatment: For optimum toughness and hardness values (without sub-zero cooling), temper the material 3 times for 1 hour/20 mm material thickness, but at least 2 hours. After each heat treatment step, cool the material to approx. 30°C [86 °F]. Achievable hardness - see tempering diagram.
Temperature	490 to 505 °C	Tempering treatment: For optimum toughness and hardness values (with sub-zero cooling), temper the material 3 times for 1 hour/20 mm material thickness, but at least 2 hours. After each heat treatment step, cool the material to approx. 30°C [86 °F]. Achievable hardness - see tempering diagram.

Physical Properties

Temperature (°C)	20
Density (kg/dm ³)	7.7
Thermal conductivity (W/(m.K))	18.2
Specific heat (kJ/kg K)	0.46
Spec. electrical resistance (Ohm.mm ² /m)	-
Modulus of elasticity (10 ³ N/mm ²)	219

Thermal Expansions between 20°C | 68°F and ...

Temperature (°C)	100	200	300	400	500
Thermal expansion (10 ⁻⁶ m/(m.K))	10.9	10.8	11.2	11.6	11.9

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25
8605 Kapfenberg, AT
T. +43/50304/20-0
E. info@bohler-edelstahl.at
<https://www.voestalpine.com/bohler-edelstahl/de/>