

OȚELURI REZISTENTE LA COROZIUNE - OȚELURI MARTENSITICE, SEMI- MARTENSITICE ȘI FERITICE

Application Segments

Inginerie

Available Product Variants

Long Products*

Plates

* Datele prezentate se referă exclusiv la produsele lungi. Vă rugăm să respectați explicațiile detaliate de la sfârșitul fișei tehnice (pdf).

Product Description

BÖHLER N360 is a corrosion resistant, martensitic stainless steel, produced using the pressurized-ESR-process (P-ESR) . Compared to conventionally produced Cr and CrMo steels, BÖHLER N360 offers improved corrosion resistance and toughness properties as well as high hardness and compressive strength.

It is typically used for anti-friction bearing components e.g. bearings, ball screws and wear resistant components for use in the engineering and medical industry, e.g. knives and other cutting tools, shafts, plastic extrusion, screw driver, drills, fasteners and engine-components, requiring resistance to both corrosion and wear with hardness not lower than 58 HRC after hardening and tempering, but usage is not limited to such applications.

Process Melting

Airmelted + PESR

Applications

- > Rulmenți
- > Instrumente de tăiere și cuțite tipice
- > Inginerie civilă și mecanică
- > Cuțit de mașină (pentru producători)
- > Vytlačanie plastov
- > Elemente de fixare, șuruburi, piulițe
- > Cuțite de mână personalizate
- > Componente pentru prelucrarea alimentelor și hrana animalelor
- > Surgery
- > Pumps
- > Componente de injecție
- > Inginerie mecanică
- > Robotics

Technical data

Material designation		Standards	
X30	Market grade	DIN SEW 400	DIN
1.4108	SEL	F899	ASTM
X30CrMoN15-1	EN		
S42027	UNS		

Chemical composition (wt. %)

C	Si	Mn	P	S	Cr	Mo	Ni	N
0.25 to 0.35	max. 1.00	max. 1.00	max. 0.030	max. 0.025	14.00 to 16.00	0.85 to 1.10	max. 0.50	0.30 to 0.50

Related to SEW 400-1.4108

Delivery condition

Recoaptă	
Hardness (HB)	max. 230 Bars max 160 mm diameter

Round Bars and Wire Rod (if any)

Diameter*	
mm	
ROLLED	
5.00	13.50
12.50	130.00

* Diameter 5.00 - 13.50 mm available as Wire Rod.

Diameter 12.5 - 130 mm round bars.

More information regarding MOQ, lengths and tolerances upon request.

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at<https://www.voestalpine.com/bohler-edelstahl/de/>