

# OȚELURI PENTRU CONSTRUCȚII - OȚELURI TRATATE TERMIC ȘI OȚELURI NITRURATE

## Available Product Variants

Plates

## Product Description

Aviation and aerospace industries, automotive, engine and gear constructions

## Applications

> Alte componente aerospațiale

> Piese structurale (aerospațiale)

## Technical data

Material designation	Standards
1.7214 SEL	S534 S535 BS
	25CD4S Others

## Chemical composition (wt. %)

C	Si	Mn	Cr	Mo
0.26	0.3	0.7	1.1	0.2

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

### voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. [info@bohler-edelstahl.at](mailto:info@bohler-edelstahl.at)

<https://www.voestalpine.com/bohler-edelstahl/de/>



ONE STEP AHEAD.