

ČELICI OTPORNI NA KOROZIJU - AUSTENITNI ČELICI I ČELICI KOJI SE NE MOGU MAGNETIZIRATI

Dostupne varijante proizvoda

Ploče

Opis proizvoda

Austenitic chromium-nickel-silicon steel with extra low carbon content.

High corrosion resistance against highly concentrated nitric acid (80 – 99,5%) or nitric acid with additions of strong oxidiser. Resistant to intergranular corrosion up to 350 °C.

Components in the chemical industry, e.g. heat exchanger, columns and acid refrigerators, Application temperature: -50°C up to 350°C, for transport and storage tanks max. 200°C.

Korištenje

- > Sklopovi za kemijska postrojenja (uklj. LNG, FGD, ureu, LDPE itd.)
- > Drugi sklopovi za naftu i plin te CPI
- > Cijevni proizvodi, priрубnice, priključci

Tehnički podaci

Oznaka materijala	
1.4361	SEL
S30600	UNS

Kemijski sastav

C	Si	Mn	Cr	Ni
≤ 0,012	4.2	0.65	17.5	15

Ako su pored šipkastih proizvoda navedene i druge dostupne varijante proizvoda, imajte na umu da se one mogu razlikovati u pogledu procesa taljenja, tehničkih podataka, stanja isporuke i površinske obrade kao i dostupnih dimenzija proizvoda. Za obvezne tehničke specifikacije, ostale zahtjeve i dimenzije molimo Vas obratiti se našim regionalnim voestalpine BÖHLER prodajnim tvrtkama. Informacije u ovom prospektu nisu obvezujuće i ne smatraju se prihvaćenima; umjesto toga, oni su samo za opće informacije. Te su informacije obvezujuće samo ako su izričito postavljene kao uvjet u ugovoru sklopljenom s nama. Mjerni podaci su laboratorijske vrijednosti i mogu se razlikovati od praktičnih analiza. U proizvodnji naših proizvoda ne koriste se tvari štetne za zdravlje ili ozon.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.