

LEGURE NA BAZI NI

Dostupne varijante proizvoda

Ploče

Opis proizvoda

Marine technique e.g. heat ex-changer and condenser up to 450°C which works with brackish- or sea water for cooling. Pickling baskets, chemical industry.

Corrosion resistant nickel-copper alloy resistant to chloride induced stress corrosion cracking. No post-weld heat treatment required. Excellent resistance to steam, torrential sea water, neutral and alkaline salt solutions. Possesses very good resistance to acid reacted salt solutions like zinc-chloride, ammonium-sulphate or ammonium-chloride as well as non oxidising acids e.g. diluted sulphuric acid, hydrochloric acid, hydrofluoric acid, silicofluoric acid, clean phosphoric acid and organic acids.

Korištenje

- Sklopovi za kemijska postrojenja (uklj. LNG, FGD, ureu, LDPE itd.)
- Drugi sklopovi za naftu i plin te CPI
- Cijevni proizvodi, prirubnice, priključci

Tehnički podaci

Oznaka materijala	
Alloy 400	Market grade
2.4360	SEL
N04400	UNS

Kemijski sastav

C	Si	Mn	Ni	Cu	Fe
0.12	0.3	1.2	65	32	1.5

Ako su pored šipkastih proizvoda navedene i druge dostupne varijante proizvoda, imajte na umu da se one mogu razlikovati u pogledu procesa taljenja, tehničkih podataka, stanja isporuke i površinske obrade kao i dostupnih dimenzija proizvoda. Za obvezne tehničke specifikacije, ostale zahtjeve i dimenzije molimo Vas obratite se našim regionalnim voestalpine BÖHLER prodajnim tvrtkama. Informacije u ovom prospektu nisu obvezujuće i ne smatraju se prihvaćenima; umjesto toga, oni su samo za opće informacije. Te su informacije obvezujuće samo ako su izričito postavljene kao uvjet u ugovoru sklopljenom s nama. Mjerni podaci su laboratorijske vrijednosti i mogu se razlikovati od praktičnih analiza. U proizvodnji naših proizvoda ne koriste se tvari štetne za zdravlje ili ozon.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.