

durostat®

MACHINERY INDUSTRY

Superior solutions made of
wear-resistant steel

 greentec
steel

Premium quality
with reduced carbon footprint

durostat®
greentec steel



durostat[®]

SUPERIOR SOLUTIONS MADE OF WEAR- RESISTANT STEEL

Highest wear resistance and hardness
for the highest stresses

Just like diamonds, durostat[®] steels stand for highest hardness. This special property of durostat[®] steels is the reason for their essentially higher resistance to wear than conventional steels. They are optimally suited to applications with high mechanical stress and high levels of abrasion. durostat[®] steels also are characterized by excellent toughness at low application temperatures.



Find out more about durostat[®]
on our website at
www.voestalpine.com/durostat





... BECAUSE
WE CARE



Stella Sustainable keeps you informed of greentec steel products, environmental protection and sustainability in the voestalpine Steel Division:
www.voestalpine.com/stella



durostat® service



durostat® efficiency




durostat® tailor welded


SEE FOR YOURSELF WHAT **durostat**[®] CAN DO FOR YOU.

For a longer service life

Service life of durostat[®]



Weight savings with durostat[®]



durostat[®] can be used in a wide variety of applications. We offer our customers the highest quality standards, yet we continually define the limits of feasibility and never lose sight of our partners' best performance. durostat[®] is a wear-resisting steel with excellent properties that have set new standards in wear resistance and hardness.

durostat[®] is now also available as a greentec steel edition in proven quality with a reduced CO₂ footprint.



Premium quality
with reduced carbon footprint

durostat[®]
greentec steel

On the following pages you will find out more about durostat[®], our wear-resistant steel for machinery. Discover what added value it can bring to your business.

- » Tipper bodies
- » Scrap containers
- » Wheel loader shovels
- » Excavators
- » Chutes
- » Truck bodies
- » Snow plows
- » Loading and conveying systems
- » and much more



durostat® service



durostat® efficiency



durostat® tailor welded

BEST PRODUCT PROPERTIES

For new standards in the machinery industry. Our durostat® steel grades set new standards with their highest quality and withstand the greatest stresses. They offer a wide variety of mechanical properties and stand for highest-quality processing. These steels can also decisively prolong the service life of your products and significantly reduce their weight.



Longer service life

We developed the durostat® product range in order to prolong the service life of your components in abrasive environments. Our steel grades have a significantly longer service life than conventional steels and withstand the most stringent environments.



Weight savings

When compared to conventional construction steels, sheet thicknesses can be significantly reduced while maintaining the same length of service life. This leads to lower dead weights and higher payloads, especially in automotive engineering.



High degree of hardness

Their high level of hardness is adjusted by means of accelerated cooling after hot rolling (direct hardening) or through conventional quenching. We prefer direct hardening because this method improves toughness and reduces scale formation. We offer unhardened steels to customers who would like to use their own heat treatment process.



Very good cold formability

Our durostat® steel grades are very well suited to cold forming, independently of whether the steel is direct-hardened or non-hardened. This is achieved through a homogeneous, fine-grained structure as well as a high degree of purity.



Good weldability

Our modern alloying strategies with optimized carbon equivalents guarantee good weldability, a factor that especially applies to direct-hardened durostat® steels. Preheating can be completely eliminated for lower sheet thicknesses.



Excellent flatness

The outstanding flatness is achieved through precisely controlled rolling processes in combination with modern leveling units. This is highly advantageous during cutting and further processing and achieves optimized dimensional accuracy of the manufactured components.



Clean surface

A uniform layer of scale forms on the sheet surface following hot rolling in our process route. The natural protective layer acts against corrosion during transport and can easily be removed through sand blasting. Selected dimensions can be supplied with a pickled surface, which makes it possible to forgo descaling prior to coating.



Premium quality with reduced carbon footprint

durostat®
greentec steel

Hot-rolled steel strip – greentec steel Edition

Max. carbon footprint 2.10 kg CO₂e per kg of steel ¹⁾

High-strength plates (excl. heads and clad plates) – greentec steel Edition

Max. carbon footprint 2.40 kg CO₂e per kg of steel ¹⁾

¹⁾ per worldsteel CML 2001-2016 (system expansion) cradle to gate

All products, dimensions and steel grades listed in each voestalpine supply range are available as greentec steel Edition.



durostat®

RANGE OF SUPPLY

Highest product quality and best processing properties distinguish durostat® steel grades. We have developed the special durostat® steel grades in order to prolong the service life of components used in abrasive environments. This service life lies significantly higher than that of conventional steels. durostat® steels withstand the most stringent environments.

Steel grade		Sheet thickness [mm]	Max. width [mm]	Max. length [mm]	Hardness reference value [HB]	Hardness guarantee value ²⁾ [HB]	Yield strength R _{0.2} reference value [MPa]	Tensile strength R _m reference value [MPa]
durostat 250		3.0 – 8.0	1,520	12,000	250	220 – 300	650	750
durostat 300		3.0 – 8.0	1,520	12,000	300	260 – 340	850	950
		8.0 – 25.0	3,000	12,000	300	270 – 350	850	950
durostat 400		2.5	1,400	12,000	400	360 – 440	1,100	1,250
		3.0	1,520					
		3.5	1,570					
		4.0 ≤ 6.0	1,620					
	> 6.0 ≤ 8.0	1,550						
		5.0 ≤ 12.0	2,500	12,000	400	360 – 440	1,000	1,250
		> 12.0 ≤ 120.0	3,000	12,000	400	360 – 440	1,000	1,250
durostat 400 toughcore®		20.0 ≤ 90.0	3,000	12,000	400	360 – 440	1,000	1,250
durostat 450		2.5	on request	12,000	450	410 – 490	1,200	1,400
		3.0	1,520					
		3.5	1,570					
		4.0 ≤ 6.0	1,620					
		> 6.0 ≤ 8.0	1,450	12,000	450	410 – 490	1,100	1,400
		> 12.0 ≤ 70.0	3,000	12,000	450	410 – 490	1,100	1,400
durostat 450 toughcore®		20.0 ≤ 40.0	3,000	12,000	450	410 – 490	1,100	1,400
durostat 500		3.0	1,450	12,000	500	460 – 540	1,300	1,550
		3.5	1,550					
		4.0 ≤ 6.0	1,600					
		8.0 ≤ 50.0	2,500	12,000	500	460 – 540	1,200	1,550
durostat B2		1.8 ≤ 15.0	1,620	12,000	500 ¹⁾	-	< 550	< 700
		8.0 ≤ 50.0	2,500	18,700	500 ¹⁾	-	400	650
durostat B4		1.5 ≤ 12.0	1,620	12,000	600 ¹⁾	-	< 600	< 800

1) Achievable hardness after quenching, supplied in non-hardened condition

2) Hardness measurements are conducted pursuant to EN ISO 6506. Test condition HBW2.5/187.5 is applied to plate thicknesses ≤ 3mm.

*) Guaranteed value at -40°C, t.s. Click here for more information on durostat toughcore: www.voestalpine.com/toughcore

Further measurements upon request.



Note

durostat 400 and durostat 450 are wear-resistant, direct-hardened carbon steels. As a heavy plate, durostat 500 is a directly or conventionally hardened steel. As a hot-rolled strip, it is a directly hardened plain carbon steel. durostat B2 and durostat B4 are supplied in non-hardened condition and are intended for heat treatment after being processed at the customer. The properties of the individual steel grades are described in the durostat® data sheets (heavy plate and hot-rolled steel strip).

Depending on the customer requirements, durostat® steel grades are supplied in direct-hardened, hardened or non-hardened condition. Both heavy plates and steel strips are accelerated-cooled directly after hot rolling. The desired hardness is adjusted to 400, 450 or 500 HB.

Elongation [A ₅] min. reference value	impact energy A _v [Joule] reference value test temperature -40 °C	Edging radii R _i min at 90° edging position of bending edge edge to rolling direction (s = sheet thickness)		delivery condition	
		longitudinal	transverse		longitudinal
12			3 s	4 s	
11			3 s	4 s	
11			3 s	4 s	directly hardened
10	50		3 s	4 s	directly hardened
10	50		3 s	4 s	directly hardened
10	40*		3 s	4 s	directly hardened
9	40		3 s	4 s	directly hardened
9	30		4 s	5 s	directly hardened
9	27*		4 s	5 s	directly hardened
8	30		3,5 s	4,5 s	directly hardened
8	20		4 s	5 s	directly hardened / hardened
> 20	-		-	-	unhardened
20	-		-	-	unhardened
> 18	-		-	-	unhardened

Cut-to-length sheets made of hot-rolled steel strip Heavy plate upon request



Conversion table

Conversion of hardness values pursuant to EN ISO 18265. This comparison serves as a reference and does not replace actual measurements or standardized conversions

400 HB	~ 420 HV10	~ 43 HRC
450 HB	~ 470 HV10	~ 47 HRC
500 HB	~ 520 HV10	~ 51 HRC



MORE THAN JUST A QUALITY PRODUCT

When solutions are in demand

We have been a reliable partner to the machinery industry for many years.

We offer innovative and sustainable product solutions and outstanding welding expertise in addition to our full service for best-possible support and process performance. State-of-the-art technologies in manufacturing and processing help reduce your costs and provide a decisive competitive advantage for your operations.

THE ADDED VALUE

OUR TECHNICAL SPECIALISTS
WILL BE HAPPY TO ADVISE
YOU WITH THEIR EXTENSIVE
EXPERTISE.



durostat® service

Our own logistics company and well stocked warehouse of sample parts in Linz make it possible for us to supply short-term trial samples for welding and bending trials. We are in a position to quickly meet your requirements and will supply small lots and cut shapes upon request. Our specialists will be happy to support you with all of your concerns.



durostat® efficiency

The material properties of durostat® steel grades and state-of-the-art quality processes eliminate revision work to the largest extent and make it possible for you to begin immediately with your production. This reduces any downtimes and increases your productivity.



durostat® tailor welded

The steel sheets used in the production of trailers, tippers and many other applications are becoming thinner and required widths larger as time progresses, and component complexity is increasing substantially. In an effort to meet these ever changing requirements, we offer laser-welded and laser-hybrid welded sheets cut from hot-rolled strip. High-quality joints:

- » Thinner, wider, more wear resistant with excellent flatness
- » Combination of different sheet thicknesses and/or material grades in one component
- » Laser/laser hybrid welded joints with perfect properties

The information and product properties contained in this printed material are non-binding and serve the sole purpose of technical orientation. They do not replace individual advisory services provided by our sales and customer service teams. The product information and characteristics set forth herein shall not be considered as guaranteed properties unless explicitly stipulated in a separate contractual agreement. For this reason, voestalpine shall not grant any warranty nor be held liable for properties and/or specifications other than those subject to explicit agreement. This also applies to the suitability and applicability of products for certain applications as well as to the further processing of materials into final products. All application risks and suitability risks shall be borne by the customer. The General Terms of Sale for Goods and Services of the voestalpine Steel Division shall apply to all materials supplied by the voestalpine Steel Division and can be accessed using the following link: www.voestalpine.com/stahl/en/The-Steel-Division/General-Terms-of-Sale

Technical changes are reserved. Errors and misprints are excepted. No part of this publication may be reprinted without explicit written permission by voestalpine Stahl GmbH.



durostat® service



durostat® efficiency



durostat® tailor welded

