



## alform® MU SERIES

### Thermomechanically rolled steels with excellent cold formability and stamped edges

The steel grades combined in the alform® MU series are microalloyed, thermomechanically rolled and characterized by excellent cold formability of stamped edges. For the alform® MU steels, mechanical-technological properties are guaranteed within narrower limits than for comparable steels pursuant to EN10149-2.

The alform® MU steels have low carbon contents and thus exhibit very good weldability. The optimized production route leads to a good limitation of non metallic inclusions and a fine-grained, homogeneous microstructure. The alform® MU steels have their advantages in particularly challenging forming operations. A good combination of cold formability and damage tolerance on stamped edges ensures increased production reliability. Improved notched bar impact energy is also achieved when compared to conventional microalloyed steels.

#### Convincing advantages

- » Narrow limits for mechanical properties
- » Very good cold formability with the narrowest bending radii, even along stamped edges
- » High damage tolerance in challenging forming operations such as flanges and collars
- » Best weldability resulting from low C equivalent
- » Excellent notched bar impact energy



Premium quality  
with reduced carbon footprint

**alform®**  
greentec steel

### Chemical composition

Ladle analysis in percent by mass and carbon equivalent

alform®	C max.	Si max.	Mn max.	P max.	S max.	Al min.	Cr max.	Ni max.	Mo max.	Cu max.	V max.	Nb max.	Ti max.	B max.	CEV max.
355 MU <sup>1)</sup>	0.10	0.10	1.20	0.018	0.005	0.020	0.3	0.3	0.08	0.3	0.05	0.05	0.05	0.003	0.28
380 MU <sup>1)</sup>	0.10	0.10	1.20	0.020	0.005	0.020	0.3	0.3	0.08	0.3	0.05	0.05	0.05	0.003	0.30
420 MU <sup>1)</sup>	0.10	0.10	1.40	0.020	0.005	0.020	0.3	0.3	0.08	0.3	0.05	0.05	0.05	0.003	0.34
460 MU <sup>1)2)</sup>	0.10	0.10	1.50	0.020	0.005	0.020	0.3	0.3	0.08	0.3	0.07	0.07	0.07	0.003	0.36
500 MU <sup>1)</sup>	0.10	0.10	1.60	0.020	0.005	0.020	0.3	0.3	0.08	0.3	0.07	0.07	0.07	0.003	0.38
550 MU <sup>1)2)</sup>	0.12	0.10	1.70	0.020	0.005	0.020	0.3	0.3	0.08	0.3	0.07	0.07	0.15	0.003	0.40

<sup>1)</sup> CEV = C + Mn/6 + (Cr+Mo+V)/5 + (Ni+Cu)/15

<sup>2)</sup> Upon request

### Mechanical properties: Tensile test

Test direction: longitudinal. minimum values for R<sub>eH</sub> und R<sub>m</sub> also apply in cross direction

R<sub>p0.2</sub> applies for the yield strength in case of missing R<sub>eH</sub>

A<sub>80</sub> for thicknesses < 3 mm

A<sub>5</sub> for thicknesses ≥ 3 mm

alform®	Yield strength R <sub>eH</sub> [MPa]	Tensile strength R <sub>m</sub> [MPa]	Total elongation [%] min.	
			A <sub>80</sub>	A <sub>5</sub>
355 MU	355 – 480	430 – 530	20	24
380 MU	380 – 510	450 – 550	20	24
420 MU	420 – 550	480 – 580	18	22
460 MU <sup>1)</sup>	460 – 590	520 – 640	16	19
500 MU	500 – 650	550 – 680	15	18
550 MU <sup>1)</sup>	≥ 550	600 – 740	14	17

<sup>1)</sup> Upon request

### Mechanical properties: Notch impact energy, edging radii, bending mandrel diameter

alform®	Notch impact energy <sup>1)</sup> KV [Joule]		Bending radii <sup>2)</sup> Ri min. at 90° edging			Bending mandrel diameter min. (transverse test specimens) sheet thickness = s
	Test temperature -20 °C	Test temperature -40 °C	s < 3 mm	s 3-6 mm	s > 6 mm	
355 MU	40	27	0.25 s	0.5 s	0.8 s	0 s
380 MU	40	27	0.25 s	0.5 s	0.8 s	0.5 s
420 MU	40	27	0.5 s	1.0 s	1.0 s	0.5 s
460 MU <sup>3)</sup>	40	27	0.5 s	1.0 s	1.4 s	1.0 s
500 MU	40	27	0.8 s	1.2 s	1.6 s	1.0 s
550 MU <sup>3)</sup>	40	27	0.8 s	1.2 s	1.6 s	1.5 s

<sup>1)</sup> KV minimum mean value from three samples (ISO-V, longitudinal) as related to full-size specimen (10 x 10 mm)

<sup>2)</sup> Smallest permissible inside radius at 90° edging. Ri min.

<sup>3)</sup> Upon request

Notch impact energy can be measured from a plate thickness of 3 mm upon request.

Note: Notch impact energy tests on thicknesses < 6 mm do not comply with respective Euronorm standards.

**Example dimensions**

Maximum width for given thicknesses

alform®	Thickness [mm]					
	2.0	2.5	3.0	3.5	4.0	6.0
355 MU	1500	1620	1620	1620	1620	1620
380 MU	1500	1620	1620	1620	1620	1620
420 MU	1360	1620	1620	1620	1620	1620
460 MU	1360	1620	1620	1620	1620	1620
500 MU	1280	1480	1620	1620	1620	1620
550 MU	1280	1480	1620	1620	1620	1620

Additional dimensions upon request.  
Depending on the dimensions and strength, we can also supply pickled, oiled or trimmed material

Steel strip	Slit steel strip	Cut-to-length sheets	Cut shapes
Width: 900 - 1620 mm	Strip widths : beginning at 30 mm	Lengths: up to 12 m	Upon request



Premium quality with reduced carbon footprint



**Hot-rolled steel strip – greentec steel Edition**

Max. carbon footprint 2.10 kg CO<sub>2</sub>e per kg of steel <sup>1)</sup>

<sup>1)</sup> per EN 15804+A2 (EPD methodology) cradle to gate

All products, dimensions and steel grades listed in each voestalpine supply range are available as greentec steel Edition.

The information and product properties contained in this printed material are non-binding and serve the sole purpose of technical orientation. They do not replace individual advisory services provided by our sales and customer service teams. The product information and characteristics set forth herein shall not be considered as guaranteed properties unless explicitly stipulated in a separate contractual agreement. For this reason, voestalpine shall not grant any warranty nor be held liable for properties and/or specifications other than those subject to explicit agreement. This also applies to the suitability and applicability of products for certain applications as well as to the further processing of materials into final products. All application risks and suitability risks shall be borne by the customer. The General Terms of Sale for Goods and Services of the voestalpine Steel Division shall apply to all materials supplied by the voestalpine Steel Division and can be accessed using the following link: [www.voestalpine.com/stahl/en/The-Steel-Division/General-Terms-of-Sale](http://www.voestalpine.com/stahl/en/The-Steel-Division/General-Terms-of-Sale)

Technical changes are reserved. Errors and misprints are excepted. No part of this publication may be reprinted without explicit written permission by voestalpine Stahl GmbH.

Please find further information and downloadable files at the following link:  
[www.voestalpine.com/alform](http://www.voestalpine.com/alform)

